

Garant
GARANT Master Steel solid carbide torus cutter HPC, TiAlN, Ø e8 DC / R1: 5/0,5mm

Order data

Order number	206333 5/0,5
GTIN	4062406276256
Item class	11X

Description
Version:

HPC milling cutter with **newly developed high-performance coating**. For **outstanding tool life** and **optimum metal removal rates** in a range of materials.

With **double relief ground side clearance angle**.

Tolerance: Corner radius R_1

Radius size 0.1 mm – 1 mm: $R_1 = \pm 0.003$ mm.

Radius size > 1.0 mm – 1 mm : $R_1 = \pm 0.005$ mm.

Application:

Especially for **high speed machining** in **mould and tool making** for **copy milling**. Excellent results for **dry milling**.

No. of teeth Z: 5

Helix angle: 30°

Shank: DIN 6535 HA to h6

No. of teeth Z: 5

Flute length L_c : 6 mm

Corner radius R_1 : 0.5 mm

Overhang length L_1 incl. recess: 18 mm

minimum shank recess dia. D_5 : 4.6 mm

maximum shank recess dia. D_6 : 4.9 mm

Technical description

Helix angle	30°
Shank	DIN 6535 HA to h6

Shank $\varnothing D_s$	5 mm
Cutting edge $\varnothing D_c$	5 mm
Feed f_z for side milling in steel < 1100 N/mm ²	0.018 mm
Overall length L	54 mm
Corner radius R_1	0.5 mm
Flute length L_c	6 mm
Feed f_z for copy milling in steel < 1100 N/mm ²	0.02 mm
Overhang length L_1 incl. recess	18 mm
No. of teeth Z	5
minimum shank recess dia. D_5	4.6 mm
maximum shank recess dia. D_6	4.9 mm
Series	Master Steel
Coating	TiAlN
Tool material	Solid carbide
Standard	Manufacturer's standard
Type	H
Tolerance nominal \varnothing	e8
Direction of infeed	horizontal, oblique and vertical
Cutting width a_e for milling operation	0.03×D for copy milling
Cutting width a_e for milling operation	0.2×D for side milling
Through-coolant	no
Machining strategy	HPC
Colour ring	green
Type of product	Torus cutter

User data

	Suitability	V_c	ISO code
Steel < 500 N/mm ²	suitable only under restricted conditions	200 m/min	P

Steel < 750 N/mm ²	suitable	170 m/min	P
Steel < 900 N/mm ²	suitable	120 m/min	P
Steel < 1100 N/mm ²	suitable	85 m/min	P
Steel < 1400 N/mm ²	suitable	70 m/min	P
Steel < 55 HRC	suitable	40 m/min	H
INOX < 900 N/mm ²	suitable	95 m/min	M
INOX > 900 N/mm ²	suitable	85 m/min	M
GG(G)	suitable	110 m/min	K
Uni	suitable		
wet maximum	suitable		
wet minimum	suitable only under restricted conditions		
dry	suitable		
Air	suitable		